Technical Data Sheet



Distributed in

The United States of America: by Peter Kwasny Inc. 62-64 Enter Lane Islandia, NY 11749 Canada: Peter Kwasny Spraypaint Canada Inc. 40 University Avenue, Suite 904 Toronto, ON. M5J 1T1

Toll free North America
Phone: 1-844-426-6330 / Fax: 1-866-226-6434
order@kwasny.us / service@kwasny.us
www.spraymax.com

SprayMax®

2K High Speed Clear

321 g NET WT. 11.3 oz

Art. Nr. 3680069



Product

Description / Purpose

2K clear coat with very short drying time and very high chemical, gasoline and weathering resistance for high quality and longterm sealing of repair paint jobs and new paint jobs on cars and motorcycles.

Properties

- · Dries very quickly
- Very smooth flow
- · Lasting high gloss
- · Maximum resistance to abrasion and scratching
- No colour deviation
- · Outstanding painting surface
- · Very good polish ability
- Suitable even at lower ambient temperatures
- · Ideally suited for small surfaces

Material base Two-component acrylic resins

Activator: aliphatic isocyanates

Colour Transparent

Gloss level gloss

90 gloss units at 20° measuring angle



Solid content

EPA Coating Category

CARB Aerosol Rule Coating Category (01/2017)

approx. 34 % by weight relating to the diluted paint

CCP Clear Coatings Product

PWR Limit 1.50

TCC Two Component Coating

PWR Limit 1.20

Substrate

Solvent and waterborne base coat systems, old paint coats dried according to manufacturer's instructions (cleaned and sanded).

Processing

Protection measures



Wear personal protection equipment.

(respiratory mask / gloves / goggles)

For more information, see safety data sheet.

Shake



Before activating, shake can thoroughly for 2 minutes

from when the mixing balls are heard.

Place red button



Remove the red button from the cap. Turn the can

by 180° and fit the button onto the pin.

Press red button



Turn the can upside down and place on a firm surface. Press the red button with the palm of your

hand until it clicks into place.

Shake



After activating, shake can again thoroughly for 2 minutes, again from when the mixing balls are heard.



After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance

Spray to test



6 - 8 inches / 15 - 20 cm



Spray passes



Dry film thickness 1.6 -2.3 mil (40 - 60 μ m) (approx. 1,5 spray coats without flash off time or 2 spray coats with flash off time)

Flash-off time



Flash time: approx. 3 min between each spray coat

Processing conditions



Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 60 %.

Coverage



approx. 3.2 - 5.8 sq ft (0,3 - 0,5 m²) / aerosol at approx.1.2 - 2.0 mil (30 - 50 μ m) dry film thickness

Drying



dust dry: 10 - 15 min dry to touch: 2 - 3 h

Ready for polishing: over night

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.



IR-drying possible, Observe equipment description 10 - 15 min flash off at room temperature, afterwards IR drying:

approx. 10 - 20 min at 60° C object temperature approx. 30 - 45 min at 40° C object temperature Ready for polishing: after cooling down and curing

Pot life



Approx. 8 h at 68° F (20° C) room temperature and a relative humidity of approx. 40 - 50 %.

The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

Finish



After painting, turn the can upside down and spray the valve until empty.



Additional Information

Shelf Life



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 68° F / 20° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.