

The United States of America:  
Peter Kwasny Inc.  
62-64 Enter Lane,  
Islandia, NY 11749

Distributed in

Canada by  
Peter Kwasny Spraypaint Canada Inc.  
2275 Lakeshore Blvd. West, Suite 530  
Toronto, ON. M8V 3Y3

Toll free North America  
Phone: 1-844-426-6330 / Fax: 1-866-226-6434  
order@kwasny.us / service@kwasny.us  
www.spraymax.com

**SprayMax®**  
**UV Spot Blender**  
**292 g NET WT. 10.3 oz**  
**Art. Nr. 3680091**



## Product

### Description / Purpose

The UV Blender is a special product for homogenous paint edges in combination with SprayMax UV Clearcoat 680059. SprayMax UV Paint Repair System is comprised of four products that complement each other to complete a repair

- UV Primer Part no 3680019
- UV Clear Part no 3680059
- UV Spot Blender Part no 3680091
- UV Primer Cleaner Part no 3680290

### Properties

- Transition-free edge zones in the blending area
- Excellent solubility properties
- No colour deviations
- Dull when dry, must be polished
- Specially for polishing

### Material base

Special solvent combination

**EPA Coating Category**

CCP Clear Coatings Product

PWR Limit 1.50

**CARB Aerosol Rule Coating Category  
(01/2017)**

CC Clear Coatings

PWR Limit 0.85

## Substrate

The surface in the sprayed transition zone should be generously matted using a sanding pad (P 2000 - P 4000).

## Processing


### Protection measures



Wear personal protection equipment.  
(respiratory mask/gloves/goggles)


For more information, see safety data sheet.

### Spraying distance




6 - 8 inches / 15 - 20 cm

### Spray passes




Directly after application of the UV clearcoat, apply several light spray coats onto the spray mist edge zone of the UV Clear 3680059 until an homogenous transition is created.

### Processing conditions



Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 60 %.

### Drying



Dry with a UV-A lamp (6 - 8 inches / 15 - 20 cm):  
2 - 4 minutes after the final spray coat and application of the blender thinner.


Dry with a UV-A LED (395nm, 120 W):

2 minutes after the final spray coat and application of the blender thinner.

The stated values refer to the above-mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.

## **Additional Information**

### **Shelf Life**



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 60° F - 77° F / 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

### **Disposal**



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

### **Note**

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.