

Technical Data Sheet



The United States of America:
by Peter Kwasny Inc.
62-64 Enter Lane
Islandia, NY 11749

Distributed in

Canada:
Peter Kwasny Spraypaint Canada Inc.
40 University Avenue, Suite 904
Toronto, ON. M5J 1T1

Toll free North America
Phone: 1-844-426-6330 / Fax: 1-866-226-6434
order@kwasny.us / service@kwasny.us
www.spraymax.com

SprayMax® 1K E-COAT Primer Field drab 318 g NET WT. 11.2 oz Art. Nr. 3680236



Product

Description / Purpose

SprayMax E Coat primers are a true direct to metal coating matching the color and gloss of factory primers and e-coat colors.
SprayMax E Coat primers provide superior corrosion protection. Perfect color and gloss match for restoring the original appearance and gloss of factory ecoats. Use E-COAT on any e-coated panel, vehicle floor, engine bay, core support, trunk area, any inner body panel.

Properties

- Superior corrosion protection
- Excellent color and gloss match to OEM factory coatings
- Direct to steel and aluminum
- Good hiding
- Available in 8 popular OEM colors
- Compatible with most automotive basecoats

Material base

Special resins

Colour

Field drab

Gloss level

Matte

Solid content	approx. 29,1 % by weight relating to the diluted paint
EPA Coating Category	ABP Auto Body Primer PWR Limit 1.55
CARB Aerosol Rule Coating Category (01/2017)	ABP Auto Body Primer PWR Limit 0.95

Substrate

Metal, Steel (cleaned and sanded).
 Aluminum (cleaned and sanded).
 E-coat (cleaned and sanded)
 Primed, filled areas and well preserved factory or old paint (cleaned and sanded).
 The damaged area must be dry and free of grease and dust and all rust needs to be removed.


Processing

Protection measures




Wear personal protection equipment.
 (respiratory mask / gloves / goggles)
 For more information, see safety data sheet.

Shake




Shake can thoroughly for at least 2 minutes from when the agitation balls are heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




6 - 8 inches / 15 - 20 cm

Spray passes



Dry film thickness 1.2 - 1.8 mil (30 - 45 µm)
 (approx. 1 - 2 spray coats)

Flash-off time




Flash time: approx. 5 - 10 min between each spray coat

Processing conditions




Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 60 %.

Coverage



approx. 5.4 sq ft (0.5 m²) / aerosol at approx. 1.2 - 1.8 mil (30 - 45 µm) dry film thickness


Drying



dust dry: 25 min
dry to touch: approx. 90 min

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.


Finish



After painting, turn the can upside down and spray the valve until empty.

Additional Information

Shelf Life



60 months
The usage period refers to an unused can that is stored correctly at a temperature of 60° F - 77° F / 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

**Note**

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.