

# Technical Data Sheet



Peter Kwasny GmbH, Heilbronner Str. 96  
74831 Gundelsheim / Germany  
Phone: +496269 95-0, Fax: +496269 95-80  
www.spraymax.com / www.kwasny.com / info@kwasny.de

## SprayMax® 2K Epoxy Primer Filler - NEW! White 400 ml Art. Nr. 680025



### Product

#### Description / Purpose

Universal 2-component epoxy primer filler for all problematic surfaces, e.g. metal, non-ferrous metals, galvanised steel or anodised aluminium.

#### Properties

- Excellent adhesion and anti-corrosion properties
- Long potlife: approx. 3 work days at 20° C
- Perfect insulation and barrier against water seepage
- Can be topcoated with all conventional paint systems
- Can be topcoated with 2K polyester

#### Material base

Two-component epoxy resins

Activator: amines

#### Colour

White

#### Gloss level

matt

#### VOC Value (EU)

645 g/l

### Substrate

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Aluminium, soft aluminium, anodised aluminium (cleaned and sanded)

FRP materials (cleaned and sanded)

Polyester surfaces (cleaned and sanded)

E-coat (cleaned and sanded)

Old paint and factory paint (cleaned and sanded)

The damaged area must be dry and free of grease and dust and all rust needs to be removed.

SprayMax 2K Epoxy Primer can be applied prior to seam sealer to complete body work.

## Processing


### Protection measures



Wear personal protection equipment.  
(respiratory mask/gloves/goggles)


For more information, see safety data sheet.

### Shake




Before activating, shake can thoroughly for 2 minutes from when the mixing balls are heard.

### Place red button




Remove the red button from the cap. Turn the can by 180° and fit the button onto the pin.

### Press red button




Turn the can upside down and place on a firm surface. Press the red button with the palm of your hand until it clicks into place.

### Shake




After activating, shake can again thoroughly for 2 minutes, again from when the mixing balls are heard.

### Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

### Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

### Spraying distance




15 cm - 20 cm

**Spray passes**



2 - 3 spray coats each approx 25 µm

**Flash-off time**




Flash time:  
approx. 5 - 10 min between each spray coat

**Processing conditions**




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

**Coverage**



approx. 1,2 m<sup>2</sup> at 20 µm  
dry film thickness

**Drying**



TG1 dust dry: 15 min  
TG3 dry to touch: 30 min  
Ready for sanding: 16 - 24 h at 20° C, 40 min at 60°C

The values given refer to the above processing conditions and a dry film thickness of 40 µm. The level of dryness is determined pursuant to DIN 53150



IR: 30 min  
Layer thickness IR-drying 30 - 40 µm  
Observe equipment description

**Continue**

Can be topcoated with all conventional 1K and 2K paints.

REMARK:


If the 2K epoxy primer is topcoated after more than 1 day, it must be sanded first.

2K UP products:

Before topcoating with a 2K filler and / or 2K spray fillers, a drying time of 16 - 24 h at room temperature or 40 minutes at 60° C needs to be respected.




Wet sanding with P 800 - P 2000




Dry sanding with P 400 - P 600

### Pot life



Up to 3 days at 20° C room temperature and a relative humidity of approx. 40 - 50 %.  
The potlife depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

### Finish



After painting, turn the can upside down and spray the valve until empty.

## Additional Information


### Important Information



Avoid bumps, friction and impact.

Do not apply to acidic primers.

### Shelf Life



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

### Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

### Note

For professional use only.  
Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.