

Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Deutschland
Telefon: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax®
1K Wheel Spray 400 ml
Art. Nr. 680040



Product

Description / Purpose

High resistant and high-yield rim spray for new and used rims

Properties

- Quick and easy to use
- Dries quickly
- Resistant to stone impact, road salt, and brake dust

Material base

Nitro combination resin

Colour

Silver

VOC Value (EU)

693 g/l

Substrate

Steelwheel (cleaned, sanded and primed)
Aluminium wheel (cleaned, sanded, primed)
Old paint and factory paint (cleaned and sanded)
Or primed with:
SprayMax® 2K Wash Primer 680029 +
2K SprayMax® Acrylic Filler 680 036, or
SprayMax® 1K Acrylic Filler 680280-680282

The damaged area must be dry and free of grease and dust and all rust needs to be removed.


Processing

Protection measures




Wear personal protection equipment.
(respiratory mask/gloves/goggles)
For more information, see safety data sheet.

Shake




Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




15 cm - 20 cm

Spray passes



Dry film thickness 30 - 40 µm
(approx. 2 - 3 spray coats)

Flash-off time




Flash time: approx. 5 min between each spray coat
End flash time: approx. 3 h

Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

Coverage



approx. 0,5 m² at 30 - 40 µm dry film thickness

Drying



TG1 dust dry: 5 min


TG5 ready for assembling: 30 min

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150

Finish




IR- drying possible,
Observe equipment description



After painting, turn the can upside down and spray the valve until empty.

Additional Information

Shelf Life



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.
Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.