

Peter Kwasny GmbH, Heilbronner Str. 96  
74831 Gundelsheim / Deutschland  
Telefon: +496269 95-0, Fax: +496269 95-80  
www.spraymax.com / www.kwasny.com / info@kwasny.de

## SprayMax® 1K Structure paint medium grey 400 ml Art. Nr. 680221



### Product

#### Description / Purpose

Special product for imitation of automotive plastic textured surfaces, particularly for plastic bumpers. Various structural finishes available. An ideal addition to the already available DTP sprays and Plastic sprays

#### Properties

- Choice of structural finishes
- Easy to use
- Dries very quickly
- Can be topcoated with all conventional 1K basecoat and 2K topcoat systems
- Also in combination with the K DTP- and Plastic sprays

#### Material base

Nitro combination resin

#### Colour

Grey

#### VOC Value (EU)

648 g/l

### Substrate

Plastics primed with SprayMax® 1K Plastic Adhesion Promotor. The damaged area must be dry and free of grease and dust and all rust needs to be removed.

## Processing

### Protection measures




Wear personal protection equipment.  
(respiratory mask/gloves/goggles)  
For more information, see safety data sheet.

### Shake




Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.

### Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

### Spraying distance




15 cm - 20 cm

### Spray passes




Dry film thickness 30 - 40  $\mu\text{m}$   
(approx. 2 - 3 spray coats)

### Flash-off time




Flash time: approx. 5 min between each spray coat

### Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

### Coverage



approx. 0,5 - 0,75 m<sup>2</sup> at 30 - 40  $\mu\text{m}$  dry film thickness

### Drying



TG1 dust dry: 5 - 10 min  
TG3 dry to touch: approx. 30 - 40 min  
TG5 fully cured: approx. 24 h / 20° C

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.



IR- drying possible,  
Observe equipment description

**Continue**


Can be topcoated with itself after 15 min and with all conventional 1K topcoats and basecoats.

## **Additional Information**

### **Important Information**

Do not spray on surfaces previously coated with synthetic resin substances as the original coat may lift.

### **Shelf Life**



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

### **Disposal**



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

### **Note**

For professional use only.  
Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.