Technical Data Sheet

Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Germany
Phone: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax®
2K Wash Primer 250 ml
Part no. 684029

Product

Description / Purpose

2 component primer for fast insulation of sanded-through areas.

Properties

- Very good adhesion
- Excellent anti-corrosion protection, in particular on aluminium
- Fast process times thanks to fine atomisation with minimum overspray
- Fast drying
- Can be topcoated with all standard 1K and 2K acrylic fillers

Material base

Polyvinylbutyral/epoxy resins. Contains phosphoric acid. Free from zinc chromate and phenol.

Colour

Olive grey

Gloss level

matt

VOC Value (EU)

703 g/l

Substrate

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Aluminium, soft aluminium (cleaned and sanded)

Polyester surfaces (cleaned and sanded)

Old paint and factory paint (cleaned and sanded)
The damaged area must be dry and free of grease and dust and all rust needs to be removed.

Processing

Protection measures

Wear personal protection equipment.
(respiratory mask/gloves/goggles)
For more information, see safety data sheet.

Shake

Before activating, shake can thoroughly for 2 minutes from when the mixing balls are heard.

Place red button



Remove the button from the cap and place it on the pin in the base of the can. Place the can with the button facing down, vertically on a firm, horizontal surface.

Press red button



Press the can down with the heel of your hand, applying even pressure. Listen for cracking sound. Only press once.

Shake

After activating the hardener, shake the spray can again for 2 minutes, again from when the mixing balls are heard.

Spray to test



After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance



15 cm - 20 cm

Spray passes



1 spray coat approx 10 - 15 µm

Flash-off time



Flash time: approx. 5 min between each spray coat.

Processing conditions

Optimum application at 18° C - 25° C
and a relative humidity from 40 - 60 %.

Coverage



approx. 3,5m² at 2 µm dry film thickness

Drying



TG3 dry to touch: 15 - 20 min / 20° C

The stated values refer to the above-mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.

Continue

When dust-dry, it can be topcoated wet-on-wet with conventional 1K or 2K acrylic fillers. In order to achieve the best possible corrosion protection, a flash time of 30 minutes (Reaction time on the metal surface) is recommended before further processing. If the Primer layer is not painted over within 8 hours, the surface shoudl be cleaned with Silicone Remover. Can be topcoated after 20 - 30 min.

Pot life



Approx. 96 h at 20 °C room temperature and a relative humidity of approx. 40 - 50 %.
The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

Finish



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.

Additional Information

Important Information

Avoid bumps, friction and impact.

Do not apply polyester and EP top coat products.
Do not use on thermoplastic paintwork.
Do not topcoat with water-based paints.
Do not apply to surfaces coated with synthetic resin paints.

Shelf Life



36 months (not activated)
The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal

The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.
For labelling see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.