

Technical Data Sheet



Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Germany
Phone: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax® 2K Rapid primer filler 250 ml Art. Nr. 684031



Product

Description / Purpose

Universal, quick-drying 2 component primer for high-quality automotive paint jobs.

Properties

- Free from isocyanates and resistant to solvents
- Quick drying
- Very good sandability,(can be wet- and dry-sanded at 20° C
- High filling capacity
- Excellent adhesion on bare metal and galvanized surfaces as well as existing sanded paint finishes
- Can be topcoated with all conventional 1K basecoat and 2K topcoat systems

Material base

Two-component acrylic resins
Activator: free from isocyanates

Colour

Grey

VOC Value (EU)

628 g/l

Substrate

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Soft aluminium (cleaned and sanded)
 Various Plastics (cleaned and sanded)
 Check compatibility and adhesion first on an unobtrusive area. If necessary prime with a suitable Plastic Adhesion Promotor.
 Polyester surfaces (cleaned and sanded)
 Old paint and factory paint (cleaned and sanded)

The damaged area must be dry and free of grease and dust and all rust needs to be removed.


Processing

Protection measures




Wear personal protection equipment.
 (respiratory mask/gloves/goggles)
 For more information, see safety data sheet.

Shake




Before activating, shake can thoroughly for 2 minutes from when the mixing balls are heard.

Place red button




Remove the red button from the cap. Turn the can by 180° and fit the button onto the pin.

Press red button




Turn the can upside down and place on a firm surface. Press the red button with the palm of your hand until it clicks into place.

Shake




After activating, shake can again thoroughly for 2 minutes, again from when the mixing balls are heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




15 cm - 20 cm

Spray passes




2 - 3 spray coats each approx 30 µm

Flash-off time




Flash time:
approx. 5 - 10 min between each spray coat
Paintable: 20 min / 20° C

Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

Coverage



approx. 0,5 - 0,75 m² at 30 - 50 µm dry film thickness

Drying



sandable: 30 min at 20° C, 15 min at 60° C

The stated values refer to the above-mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.




IR: 16 min
Observe equipment description

Continue

Can be topcoated wet -on-wet with all conventional 1K and 2K topcoats after approx. 20 min.




Wet sanding with P 800




Dry sanding with Excenter and P 400

Pot life



Approx. 24 h at 20° C room temperature and a relative humidity of approx. 40 - 50 %.
The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

Finish



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.


Additional Information

Important Information



Avoid bumps, friction and impact.

Shelf Life



36 months (not activated)
The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.
For labelling see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.