

Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Deutschland
Telefon: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax® 2K Acrylic filler 250 ml Art. Nr. 684036



Product

Description / Purpose

Very fast-drying 2 component filler with excellent filling capacity, outstanding flow, and very effective isolation for old paint jobs. Preprime sand-through areas, with a 2K Washprimer or a 1K Primer Filler for example.

Properties

- High layer thickness and very good pore filling
- Dries very quickly, ideally suited to IR drying
- Very good, easy sandability
- Maximum mechanical strength
- Can be topcoated with all conventional 1K basecoat and 2K topcoat systems, particularly suited to water-borne basecoats

Material base

Two-component acrylic resins
Activator: aliphatic isocyanates

Colour

Medium grey

VOC Value (EU)

620 g/l

Substrate

Steel (cleaned and sanded)
FRP materials (cleaned and sanded)
Polyester surfaces (cleaned and sanded)
E-coat (cleaned and sanded)

Old paint and factory paint (cleaned and sanded)
 The damaged area must be dry and free of grease
 and dust and all rust needs to be removed.


Processing

Protection measures




Wear personal protection equipment.
 (respiratory mask/gloves/goggles)
 For more information, see safety data sheet.

Shake




Before activating, shake can thoroughly for 2 minutes
 from when the mixing balls are heard.

Place red button




Remove the red button from the cap. Turn the can
 by 180° and fit the button onto the pin.

Press red button




Turn the can upside down and place on a firm
 surface. Press the red button with the palm of your
 hand until it clicks into place.

Shake




After activating, shake can again thoroughly for
 2 minutes, again from when the mixing balls are
 heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and
 pattern of the damage.

Spray to test




After shaking the can, test spray and check
 compatibility with the surface and the colour.

Spraying distance




15 cm - 20 cm

Spray passes



2 - 3 spray coats each approx. 20° C

Flash-off time




Flash time: approx. 5 min between each spray coat (until matt)
 Paintable: 10 - 15 min / 20° C

Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

Coverage



approx. 5 m² at 30 µm dry film thickness

Drying



TG1 dust dry: 5 min
 TG3 dry to touch: 20 min
 Ready for sanding: 3 - 4 hours / 20° C
 The stated values refer to the above-mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.




IR: 25 min.
 Observe equipment description

Continue

Can be topcoated with all conventional 1K or 2K top coats, and solvent and water-based paints.




Wet sanding with P 800 - P 1200




Dry sanding with P 600 - P 1000

Pot life



Approx. 24 h at 20° C room temperature and a relative humidity of approx. 40 - 50 %.
 The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.


Finish



After painting, turn the can upside down and spray the valve until empty.

Additional Information


Important Information



Avoid bumps, friction and impact.

Larger sandthrough areas should be primed with SprayMax® 1K Primer Shade or SprayMax® 2K EP Primer Fillers.

Shelf Life



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.