

Technical Data Sheet



Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Germany
Phone: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax®
2K Quick Epoxy Primer grey
250 ml
Art. Nr. 684265



Product

Description / Purpose

Universal 2K Quick Epoxy Primer filler for all problematic surfaces, e.g. metal, non-ferrous metals, galvanised steel or anodised aluminium.

Properties

- Excellent adhesion and anti-corrosion properties
- Accelerated drying
- Perfect insulation and barrier against water seepage
- Can be topcoated with all conventional paint systems
- Can be topcoated with 2K polyester

Material base

Two-component epoxy resins

Activator: amines

Colour

grey

VOC Value (EU)

approx. 640 g/l

Substrate

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Aluminium, soft aluminium, anodised aluminium (cleaned and sanded)

FRP materials (cleaned and sanded)
 Polyester surfaces (cleaned and sanded)
 E-coat (cleaned and sanded)
 Old paint and factory paint (cleaned and sanded)

The damaged area must be dry and free of grease and dust and all rust needs to be removed.
 SprayMax 2K Quick Epoxy Primer can be applied prior to seam sealer to complete body work.


Processing

Protection measures




Wear personal protection equipment.
 (respiratory mask/gloves/goggles)
 For more information, see safety data sheet.

Shake




Before activating, shake can thoroughly for 2 minutes from when the mixing balls are heard.

Place red button




Remove the button from the cap and place it on the pin in the base of the can. Place the can with the button facing down, vertically on a firm, horizontal surface.

Press red button




Press the can down with the heel of your hand, applying even pressure. Listen for cracking sound. Only press once.

Shake




After activating the hardener, shake the spray can again for 2 minutes, again from when the mixing balls are heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




15 cm - 20 cm

Spray passes




2 - 3 spray coats approx. 25 µm each

Flash-off time




Flash time:
approx. 5 - 10 min between each spray coat

Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

Coverage



approx. 0,5 m² at 40 µm
dry film thickness

Drying



Ready for sanding:
approx. 11 h at 20° C, 60 min at 60° C
The stated values refer to the above-mentioned processing conditions and a dry film thickness of 40 µm. The level of dryness is determined pursuant to DIN 53150.



IR: 25 min.
Layer thickness IR drying: 30 - 40 µm
Observe equipment description

Continue

Can be topcoated after approx. 20 minutes with all conventional 1K and 2K paints.


REMARK:

If the 2K Quick Epoxy Primer is topcoated after more than 1 day, it must be sanded first.


2K UP products:

Before topcoating with a 2K filler and / or 2K spray fillers, a drying time of 11 h at room temperature or 60 minutes at 60° C needs to be respected.

Pot life




Dry sanding with P 400 - P 600



8 h at 20° C room temperature and a relative humidity of approx. 40 - 50 %.

The potlife depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

Finish



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.

Additional Information


Important Information



Avoid bumps, friction and impact.

Do not apply on acidic primers.

Shelf Life



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

For labelling see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.