

Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Deutschland
Telefon: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

SprayMax®
1K Clearcoat Gloss 400 ml
Art. Nr. 690300



Product

Description / Purpose

1K clear coat for sealing and protecting painted surfaces. For fast painting of small surfaces on untreated, glazed or coloured surfaces or wood, timber, iron or steel.

Properties

- Universal
- Fast-drying
- Good polishing properties, glossy
- Does not turn yellow
- Weather resistant
- For indoors and outdoors

Material base

Acrylic resins

Gloss level

gloss

VOC Value (EU)

685 g/l

Substrate

All surfaces

The damaged area must be dry and free of grease and dust and all rust needs to be removed.


Processing

Protection measures




Wear personal protection equipment.
(respiratory mask/gloves/goggles)
For more information, see safety data sheet.

Shake




Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




15 cm - 20 cm

Spray passes




Dry film thickness 30 - 40 µm
(approx. 2 - 3 spray coats)

Flash-off time




Flash time: approx. 5 - 10 min between each spray coat

Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

Coverage



approx. 1,3 - 1,5 m² at 40 µm dry film thickness


Drying



TG1 dust dry: 10 min
TG3 dry to touch: 20 min
Ready for polishing: approx. 12 hours

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.


Finish



After painting, turn the can upside down and spray the valve until empty.

Additional Information

Shelf Life



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.