

Technical Data Sheet

Peter Kwasny GmbH, Heilbronner Str. 96
74831 Gundelsheim / Germany
Phone: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

Auto-K paint preparation Filling putty (styrene-reduced)

1000 g

Art. Nr. 745402



Product

Description / Purpose

For levelling and filling unevenness on car bodies, objects made of metal, stone, concrete, plastic, ceramics and wood. Can also be used as a filler layer over glass fibre filler.

Properties

- Excellent adhesion on roughened, dry surfaces
- Easy to apply
- Easy to sand
- Cures without cracking and shrinkage
- For smooth, non-porous surfaces
- Can be used as a filler layer over glass fibre filler

Material base

Polyester resins

Colour

light grey (without hardener)

Substrate

Metal, stone, concrete, plastic, ceramic and wood


Processing

Protection measures




Wear personal protection equipment.
(gloves / goggles)
For more information, see safety data sheet.

Processing conditions




Optimum application at 18° C - 25° C.
The substrate must be dry and free of dust and grease.

Coverage



PU 1000 g in set with hardener: 2 pieces per carton

Drying



Sandable after: 20 min at 20° C

Continue

Carefully clean the substrate of dust, grease and release agent and sand it. Thoroughly mix the required amount of filler with 2% hardener in the plastic lid and apply quickly.

Pot life

approx. 5 min at 20° C

Finish


Please clean any tools used (spatula blade, mixing cup, etc.) immediately after finishing work (e.g. with acetone / nitro thinner).

Additional Information

Important Information

CAUTION!
Do not return mixed filler back into the can.

Shelf Life



Filler and hardener 1 year at 20° C in the original closed sealed container when stored properly in a dry place.

Disposal



Can and tube with cured material must be disposed of as hazardous waste.

Note

Before use, the safety instructions must always be read carefully and observed.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.