

# **Technical Data Sheet**

Peter Kwasny GmbH, Heilbronner Str. 96 74831 Gundelsheim / Germany Phone: +496269 95-0, Fax: +496269 95-80 www.spraymax.com / www.kwasny.com / info@kwasny.de

Auto-K paint preparation 2-component polyester repair resin (styrene reduced) 250 g

Art. Nr. 745450

## **Product**

Art.Nr. 745450

Page 1

Description / Purpose	For processing the glass fibre materials for small and large damages. Removal of rust-through, cracks or holes on car bodies, caravans, boats, surfboards, gutters, pipes, etc. Apply fibreglass material soaked in resin to the repair area. Several layers can be laminated on top of each other. Only use glass fibre material (mat, fabric or fleece) process. The material can be filled over and (after sanding) painted over.
	sanding) painted over.
Properties	<ul> <li>Adaptation to existing moulds</li> <li>Application friendly problem solving</li> <li>Fast curing</li> <li>Water and solvent resistant</li> <li>Petrol resistant</li> <li>Hardening of resin and filler without cracking or shrinkage (in compliance with the prescribed hardener quantities)</li> </ul>
Material base	Polyester resins
Colour	yellow transparent
<u>Substrate</u>	
	Metals, sheet metal
	(cleaned, sanded, free of and grease)
	Plastics (cleaned, free of dust and grease)

Version 7/2023



## Processing

**Protection measures** 

**Processing conditions** 

Coverage

Drying

#### Continue

Pot life

Finish

## **Additional Information**

**Important Information** 

Wear personal protection equipment. (gloves / goggles) For more information, see safety data sheet.



Optimum application at 18° C - 25° C. The substrate must be dry and free of dust and grease.

PU 250 g: 6 pieces per carton



Processing time: approx. 5 - 10 min. (at 20° C) fully dried: approx. 20 - 30 min. (at 20° C)

All impurities must be cleaned with Nitro Universal Thinner before curing.

Mix the amount of resin that can be used within the pot life with 2 % hardener.

Apply fibreglass material soaked in resin to the repair area. Several layers can be laminated on top of each other. The material can be filled over and (after sanding) painted over.

At 20° C approx. 10 min.

Close the jar airtight with the lid and the tube with the plastic cap. Observe instructions on the product.

Only use glass fibre material (mat, fabric or fleece). All impurities must be cleaned with Nitro Universal Thinner before curing.

Do not return the mixed material back into the can. Use gloves.

Please clean any tools used (spatula blade, mixing cup, etc.) immediately after finishing the work (e.g. with acetone / nitro thinner).

Version 7/2023



### Shelf Life

Disposal

Note

Shelf life at least 1 year if stored properly, dry and airtight at 20° C.

Cans with cured material are to be disposed of as hazardous waste.

Before use, the safety instructions must always be read carefully and observed.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.