

Technical Data Sheet

Peter Kwasny GmbH, Heilbronner Str. 96
 74831 Gundelsheim / Germany
 Phone: +496269 95-0, Fax: +496269 95-80
www.spraymax.com / www.kwasny.com / info@kwasny.de

Auto-K paint preparation Plastic filler (styrene-reduced)

250 g
Art. Nr. 745470



Product

Description / Purpose

Styrene-reduced 2-component plastic filler on a Polyester resin-based. For smoothing and filling depressions and scratches on plastic parts such as GRP. Universally applicable for most plastics (check compatibility), but also suitable for wood, iron, steel, aluminium etc.

Properties

- Very good adhesion to plastics, e.g. GRP, PU, ABS, PVC, PC, PA etc.
- Very good sandability (after 30 min.)
- Universally applicable on steel, iron, aluminium, wood, concrete, ceramics etc.
- Can be applied easily and without pores
- Cures without cracking and shrinkage
- Can be painted over with all commercially available 1K topcoat systems

Material base

Specific polyester resin

Colour

dark grey (without hardener)

Substrate

Steel, iron, aluminium
 Plastics such as GRP, PU, ABS, PVC, PC, PA etc.
 Wood, ceramics, concrete etc.
 (substrates must be clean, dry and free of grease)


Processing

Protection measures




Wear personal protection equipment.
(gloves / goggles)
For more information, see safety data sheet.

Processing conditions




Optimum application at 18° C - 25° C.

Coverage



PU 250 g in set with hardener: 6 pieces per carton

Drying



fully dried: after approx. 20 - 30 h.
can be painted over: after 30 min.
sandability: after 20 - 30 min at 20° C

Pot life

approx. 4 - 5 min at 20° C

Finish


Please clean any tools used (spatula blade, mixing cup, etc.) immediately after finishing work (e.g. with acetone / nitro thinner).

Additional Information

Important Information

CAUTION!
Do not return mixed filler back into the can.

Shelf Life



Filler and hardener 1 year at 20° C in the original closed sealed container when stored properly in a dry place.

Disposal



Can and tube with cured material must be disposed of as hazardous waste.

Note

Before use, the safety instructions must always be read carefully and observed.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.